

CARTONE STRALIS PLUS

Dati tecnici

GRAMMATURA	SPESSORE μ	BULK cc/gm	L&W resistenza al piegamento, Nm		
			MD	CD	GM
T 410	T 411		T 556		
190	278	1,46	110	55	78
200	296	1,48	130	65	92
210	311	1,48	145	73	103
220	326	1,48	175	88	124
230	341	1,48	190	95	134
250	370	1,48	260	130	184
270	404	1,50	360	180	255
280	420	1,50	380	190	269
290	445	1,54	430	215	304
300*	462	1,54	500	250	354
320	499	1,56	580	290	410
330	515	1,56	680	340	481
340	529	1,56	700	350	495
350*	551	1,58	730	365	516
400	630	1,58	960	480	679
Tolleranza \pm 3%	\pm 4%		\pm 10%		

PROPRIETA'		Unità di m.	VALORE	STANDARDS
Roughness (PPS) Top	200 – 250 gsm	μ	1,3 ± 0,2	T 555
	>251 gsm		1,5 ± 0,2	
IGT Dry Pick (MV)	top	m/s	1,2 ± 0,2	ISO 3782
Gloss at 75°, min	top	%	40 min	T 480
ISO Brightness	top	%	89 ± 2	ISO 2470
CIE Whiteness, min	top	%	120 min	ISO 11475
Scott Ply Bond		j/m2	> 150	T 569
Cobb ₆₀	top	g/m2	30 ± 5	T 441
	Back		35 ± 5	
Moisture	< 300	%	6,0 – 7,0	T 412
	> 301		6,5 – 8,5	
Shade			Light Reddish Blue	Under D65 Light Source

NOTE

Test Conditions: Temperature 23 ± 1°C & Relative Humidity 50± 2%. (Tappi 402)

All Parameters are measured as per the relevant Tappi & ISO standards.